

# Sepulchre Minerals

## Zirconium Silicate Beads (burned)

**Description:** King's Zirconium Silicate Beads are produced by using a burning method. They have designed especially for milling of zirconium silicate and magnesium- aluminum silicate.

**Specification:**

Content of ZrO <sub>2</sub> , (%)	> 40
Theoretical specific weight	3.65
Real specific weight	3.6
Bulk density	2.9
Hardness, (Mohs)	8
Disc speed, (m / sec)	10 (max.)
Sizes available, Ø (mm):	0.5 - 10

**Packaging:** 20 kg net in plastic drums or 500 kg in big bag